IN THE CLAIMS

Please amend the claims as follows:

(CURRENTLY AMENDED) A portable heating pack comprising:

a supercorroding metallic alloy powder <u>disposed within said</u>

<u>portable heating pack</u>, <u>said supercorroding metallic alloy powder</u>

<u>adapted to produce producing</u> heat and gaseous hydrogen upon contacting a corroding liquid; <u>and</u>

means for consuming and/or storing said gaseous hydrogen in gaseous communication with said supercorroding metallic alloy powder; and

means for contacting said supercorroding metallic alloy powder with a corroding liquid.

- 2. (ORIGINAL) The portable heating pack according to claim 1, wherein said portable heating pack further comprises means for conducting heat produced within said portable heating pack to the exterior of said portable heating pack.
- (ORIGINAL) The portable heating pack according to claim
 wherein said supercorroding metallic alloy is a magnesium-iron
 alloy.
- 4. (CURRENTLY AMENDED) A portable heating pack comprising:

 a supercorroding metallic alloy adapted to produce heat and

gaseous hydrogen upon contacting a corroding liquid; and

The portable heating pack according to claim 1, wherein said means for consuming and/or storing said gaseous hydrogen comprise a hydrogen storage material adapted to absorb said gaseous hydrogen.

- 5. (CANCELED)
- 6. (CANCELED)
- 7. (CURRENTLY AMENDED) The portable heating pack according to claim 6 4, wherein said hydrogen storage material is intimately mixed with said supercorroding metallic alloy.
 - 8. (CANCELED)
- 9. (ORIGINAL) The portable heating pack according to claim 4, wherein said hydrogen storage material is selected from AB, A_2B , AB_2 , or AB_5 type alloys.
- 10. (ORIGINAL) The portable heating pack according to claim 4, wherein said hydrogen storage material is selected from Mg alloy systems, Mg-Ni alloy systems, Mg-Cu alloy systems, Ti-Fe alloy systems, Ti-Mn alloy systems, Ti-Ni alloy systems, Ti-V alloy

systems, Ti-Cr alloy systems, Mm-Ni alloy systems, Mm-Co alloy systems, or combinations thereof.

- 11. (CURRENTLY AMENDED) The portable heating pack according to claim 4, wherein said portable heating pack means for consuming and/or storing said gaseous hydrogen further comprises comprise an oxide material adapted to consume said gaseous hydrogen via a reduction reaction, said oxide material being in gaseous communication with said gaseous hydrogen.
- 12. (ORIGINAL) The portable heating pack according to claim 11, wherein said oxide material is intimately mixed with said supercorroding metallic alloy powder.
- 13. (ORIGINAL) The portable heating pack according to claim 11, wherein said oxide material is an oxide of at least one metal selected from copper, silver, manganese, nickel, zinc, cadmium, or mercury.

14. (CANCELED)

15. (CURRENTLY AMENDED) The portable heating pack according to claim 4, wherein said portable heating pack 1 further comprises comprising a high surface area carbon intimately mixed with said

supercorroding alloy powder.

16. (CURRENTLY AMENDED) A portable heating pack comprising:

a supercorroding metallic alloy adapted to produce heat and
gaseous hydrogen upon contacting a corroding liquid; and

PATENT DEPT

The portable heating pack according to claim 1. wherein said

means for consuming and/or storing said gaseous hydrogen comprise

an oxide material adapted to consume said gaseous hydrogen via a
reduction reaction, wherein the oxide material is in gaseous

communication with the gaseous hydrogen.

- 17. (ORIGINAL) The portable heating pack according to claim 16, wherein said oxide material is intimately mixed with said supercorroding metallic alloy powder.
- 18. (ORIGINAL) The portable heating pack according to claim 16, wherein said oxide material is an oxide of at least one metal selected from copper, silver, manganese, nickel, zinc, cadmium, or mercury.
 - 19. (CANCELED)
 - 20. (CANCELED)